

DETECTAMET

Technical Data Sheet

Document Reference	410
Date of Issue	2 nd Dec 2024
Revision Number	003
Date of Last Revision	17 th Feb 2026

410 2 Flange Reusable Earplugs



Technical Data Sheet Applicable To:

410-P20-S101-X18	Metal Detectable 2 Flange Reusable Earplugs with cord Blue pack of 200
415-S101-P01-X18	Metal Detectable 2 Flange Reusable Earplugs Uncorded Blue Pack of 200

Industry Usage:

These earplugs are suitable for use in loud environments within food factories, helping to protect your hearing in certain situations.

Features and Benefits:

- Metal detectable & X-ray visible earplug & cord
- Available loose or corded
- Cord length: 600mm (23.62")
- SNR Rating: 23db
- Durable and Non-Toxic

Material and Compliance information:

Property	Units	Typical Value	Test Method
Hardness	Shore A	67	ASTM D2240
Tensile Strength	MPa	9.0	BS ISO 37
Elongation to Break	%	340	BS ISO 37
Tear Strength	N/mm	15.7	BS ISO 34-1 method C

Compression Set 25% for 24hrs @ 150c	%	14.1	BS 903 pt A6 type B
---	---	------	---------------------

Magnetic Pull	Mm	6.5	SWEI/700 ISS 2
Temperature	C	-60 to 200	

Colour Dark Blue 60 Shore

The above product contains only ingredients that are listed by the American food and drugs administration (FDA) under the 21 CFR number 177-2600 & EC 1935/2004

Technical Report

Testing Requirements

Regulation 2016/425 Module C2 limited testing of 3-flange earplugs described as 410-P20-S120-X18 in accordance with EN 352-2:2020

Work requested

Samples of ear-plugs, reference 410-P20-S101-X18 were received by a third party tested for Module C2 testing in accordance with BS EN 352-2:2020 Hearing protectors – General requirements ; Part 2: Ear-plugs Clause 4.1 and Sizing and adjustability and 4.3.6 Minimum attenuation.

Conclusions

Standard	Clause/Property	Result
BS EN 352-2:2020	4.1 Sizing and Adjustability	Pass
	4.3.6 Minimum Attenuation	Pass

Testing

Testing was carried out in accordance with BS EN 352-2:2020

Unless otherwise specified either in the individual test method or in this report, samples were tested 'as received', after conditioning, and tested under normal ambient conditions.

The average mass of the samples was 4.61g

Test results

Clause/Test	Requirement	Test Results	Result
4.1.1. Sizing and adjustability. Aural ear-plugs	The nominal diameter or, if appropriate, the range of nominal diameters of the earplugs shall be tested in accordance with EN 13819-1:2002, 5.2 and reported.	The ear-plugs fit the sizing specification from 9.0mm to 11.0mm	Pass
4.3.6 Minimum attenuation	When tested in accordance with EN 13819-2:2002, 4.2, the values (Mf – Sf) of the earplugs shall not be less than the values shown in table 1 of BS EN 352-2:2020. See note 1.	The earplugs met the minimum attenuation of requirements of BS EN 352-2:2020 (see Appendix A)	Pass

Additional information / Notes

Table 1 of BS EN 352-1:2002

Frequency (Hz)	125	250	500	1000	2000	4000	8000
Mf-Sf (dB)	5	8	10	12	12	12	12

Uncertainty of measurement is detailed in the table below. Test where estimated Uncertainty of measurement is applied at point of test (e.g. to applied force or to tolerance limits) to ensure product meets requirements of the standard are detailed.

Additional uncertainty of measurement information

Clause/test	Property	UoM
4.1 Sizing and adjustability	Weight	+/- 0.0022g
4.3.6 Minimum attenuation	Assumed Protection Values	20% of minimum result

Appendix: Subjective attenuation testing

Introduction

BS EN 24869-1:1993 (ISO 4869-1:1990) specifies a subjective method for measuring the attenuation of hearing protection at the threshold of hearing. This method was applied to the samples provided for testing.

Test subjects

The testing was conducted on sixteen test subjects, as specified by the test standard. The subjects comprised both males and females over a wide range of ages. All subjects were audiometrically screened in accordance with clause 4.4.1 of BS EN 24869-1:1993 prior to the test

Fitting

Manufacturer's instructions were provided to the test subjects and followed during the fitting of the device. Guidance was also available from the test engineer.

Test Procedure

The procedure specified in BS EN 24869-1:1993, 4.5 was followed

		Frequency (Hz) / Attenuation (dB, re. 2×10^{-5} Pa)							
Subject	Sample	63	125	250	500	1000	2000	4000	8000
A	1	6	6	8	8	14	26	26	26
B	2	24	20	20	22	28	38	34	30
C	3	22	20	26	26	26	34	38	32
D	4	32	32	26	28	24	32	34	36
E	5	28	22	22	20	34	28	36	36
F	6	34	24	24	32	32	36	44	36
G	7	18	20	24	16	24	36	32	44
H	8	22	30	26	28	28	32	48	48
I	9	24	24	24	24	24	32	30	24
J	10	26	28	22	28	26	32	46	40
K	11	18	16	18	26	26	36	42	34
L	12	18	14	18	22	20	24	28	28
M	13	28	24	28	30	32	38	48	38
N	14	16	22	18	18	18	24	36	32
O	15	8	8	14	18	20	26	26	22
P	16	20	22	22	22	24	36	40	42

Mean Attenuation	21.5	20.8	21.3	23.0	25.0	31.9	36.8	34.3
Standard deviation	7.6	7.1	5.2	6.1	5.3	4.9	7.4	7.3
Assumed protection (a=1)	13.9	13.7	16.1	16.9	19.7	27.0	29.4	27.0
Assumed protection (a=2)	6.3	6.6	10.9	10.8	14.4	22.1	22.0	19.7

Subject	Sample	H	M	L	SNR
A	1	21.5	12.8	9.4	16.2
B	2	33.0	26.3	22.6	29.1
C	3	32.5	27.5	25.7	30.6
D	4	30.9	26.4	26.6	29.8
E	5	30.7	25.9	22.9	28.5
F	6	36.7	32.2	27.6	34.7
G	7	20.7	21.8	20.2	25.5
H	8	33.6	29.2	28.30	32.5
I	9	28.0	25.3	24.6	27.3
J	10	32.7	27.6	25.5	30.9
K	11	33.7	26.4	21.1	29.4
L	12	24.7	21.5	19.4	24.1
M	13	38.0	32.6	29.4	35.5
N	14	24.6	19.5	18.9	23.0
O	15	24.4	20.0	15.1	22.2
P	16	32.4	25.0	23.2	28.7
Mean attenuation		30.5	25.0	22.5	28.0
Standard deviation		4.7	5.0	5.2	4.9
Assumed protection (a=1)		25.8	20.0	17.3	23.1
Nominal value		26	20	17	23

No warranty is given or implied with respect to this information or patent infringement. Detectamet Ltd do not accept liability for loss or damage arising from the use of this information. Results are based on a test sample, our general experience and information from suppliers. Data and results may be confirmed by the buyer by testing for its intended conditions of use.

Safety You Detect

detectamet.global

